

אריח אנטי וייב - מדברי חום שעם

1000 × 1000 × 20 mm

מידות במ"מ: אורך × רוחב × עובי

STU20-CR-100/100.2636



1 m²

שטח אריח

1,000 kg/m³

צפיפות לפי נתון המשתמש

20 mm

עובי נומינלי

הרכב החומר

שכבה עליונה: גרגירי גומי ממוחזרים מסוליות נעליים.

SBR + EPDM

שכבה תחתונה: גומי ממוחזר מסוג

"שעם" הוא חלק משם הגוון המסחרי; החומר הוא גומי, ללא שעם טבעי.

מידות, התקנה ויישומים

סבולת אורך ורוחב: עד אחוז וחצי לכל כיוון; סבולת עובי: שני מ"מ לכל כיוון.

לפי מפרט הסדרה: חדרי כושר, מגרשי משחקים וגני ילדים.

התקנה באמצעות מחברים או בהדבקה, בהתאם להנחיות היצרן.

הערות לנתונים

הצפיפות מבוססת על נתון המשתמש ובהנחת יחידת ק"ג למ"ק.

היא אינה מופיעה במפרט היצרן המצורף. משקל האריח לא צוין במקור,

ולכן אינו מוצג. במפרט אין נתוני ביצועי בידוד רעידות.

נתוני הבדיקות בעמוד הבא הם נתוני הסדרה המדווחים במפרט היצרן.

RECYCLED RUBBER TILE

Desert brown / cork-look colour

Nominal size: 1000 × 1000 × 20 mm | Coverage: 1 m² / tile

Material construction

Top layer: recycled sole rubber granules.
Bottom layer: recycled SBR + recycled EPDM, random multicolour.
The commercial colour name refers to appearance; the material is rubber.

Manufacturer-reported series test data

Source: Guangdong Berson New Materials Co., Ltd. - BS-9000 technical data.

Property	Standard	Result
Tear strength	ISO 34-1	15 kN/m
Tensile strength	ASTM D412	2.07 MPa
Elongation at break	ASTM D412	33%
Abrasion resistance	ISO 4649	252.6 mm³
Slip resistance	DIN EN 16165	R10
Resistance to chemicals	EN ISO 26987	Pass
Static coefficient of friction	ASTM D2047	Dry: 0.75 / Wet: 0.78
Residual indentation	EN ISO 24343	0.38 mm
Static load limit*	ASTM F970	0.27 mm

*Source property label retained; the reported result is a deformation in mm.

Dimensions & installation

Length/width tolerance: ±1.5%; thickness tolerance at 20 mm: ±2 mm.
Source-listed uses: gym, playground, kindergarten. Fixing: connectors or glue down.

Data basis & limitations

Density: 1,000 kg/m³, interpreting user input “1000KGM” as kg/m³.
User-supplied value; density is not stated in the attached Berson specification.
Tile mass is not stated in the supplied source and is therefore not reported.
The source reports series values; it does not establish SKU-specific certification.
No vibration-isolation performance or certification is asserted by this data sheet.